

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**AMENDMENTS TO THE SPECIFICATION**

**Replace page 6 last full paragraph with the following new paragraph:**

According to the maraging steel, oxide-base non-metallic inclusions can be reduced in size and amount (i.e. the amount is that of large oxide inclusions each having a size of more than 20  $\mu\text{m}$ ). It is also possible to reduce the size of nitride-base non-metallic inclusions ~~such as TiC and TiCN~~such as TiN and TiCN. Thus, the maraging steel has an improved fatigue strength.

**Replace page 33, first full paragraph with the following new paragraph:**

From the above-described results, it has been seen that in the maraging steel of the present invention, the oxide-base non-metallic inclusions can be reduced in size and amount and that it is also possible to reduce the sizes of the nitride-base non-metallic inclusions ~~such as TiC and TiCN~~such as TiN and TiCN and that the maraging steel has a superior fatigue strength.

**Replace page 33, last full paragraph with the following new paragraph:**

When the method of producing the maraging steel of the present invention is applied, the oxide-base non-metallic inclusions can be reduced in size and amount, it is also possible to reduce the sizes of the nitride-base non-metallic inclusions ~~such as TiC and TiCN~~such as TiN and TiCN, and the present invention is optimum for the application requiring a strict fatigue strength. The present invention is optimum for the representative application such as the component for the continuously variable transmission of the automobile engine.